



ICETHIN: CLEAR EPOXY CASTING TECHNICAL DATA SHEET

DESCRIPTION

ICETHIN is a two component epoxy casting system. UV resistant, it has anti-yellowing properties, strong adhesion, good fluidity, natural defoaming. **It is used for top coating or light casting with thicknesses from 1/16 inch (1.6 mm) to 1 inch (2.5 cm).** The low color and low viscosity allow for bubble free, crystal clear castings ideal for art and hobby applications. It is formulated for a long gel time, with low exothermic heat buildup. ICETHIN has a low VOC content, for user safety and reduced environmental impact.

PRIMARY APPLICATIONS

- Embedding and encapsulation
- Resin jewelry
- Small castings
- Bar, table or counter top coat
- Molding resin
- Art or crafting resin

TECHNICAL SPECIFICATIONS AND MECHANICAL DATA

COLOR	Clear
MIX RATIO, BY VOLUME	1 : 1 (RESIN: HARDENER)
MIX RATIO, BY WEIGHT	1 : 0.83 (RESIN: HARDENER)
VISCOSITY @ 73°F (23°C)	A = 5000 - 8000 cps B = 500- 1000 cps Mixed: 2500 - 3500 cps
POT LIFE	30 minutes @ 68°F (20°C)
INITIAL CURE TIME	12-14 hours @ 32 - 50°F (0 - 10°C) 6 - 8 hours @ 50 - 59°F (10 - 15°C) 3 - 5 hours @ 59 - 77°F (15 - 25°C)
COMPLETE CURE TIME	48 hours @ 32 - 50°F (0 - 10°C) 36 hours @ 50 - 59°F (10 - 15°C) 8 - 10 hours @ 59 - 77°F (15 - 25°C)
IDEAL WORKING TEMPERATURE RANGE	OPTIMAL 59 - 70°F (15 - 21°C)
MAXIMUM CASTABLE AMOUNT	0,5 gallon (2 L)
PEAK EXOTHERM	100°F (38°C)
TENSILE STRENGTH	9500 PSI
ELONGATION	6.7%
FLEXURAL STRENGTH	15500 PSI
COMPRESSION STRENGTH	8.4 kg/mm ²
TG ULTIMATE	203°F (95°C)
HARDNESS, SHORE D	82
VOC	0 g/L

IMPORTANT NOTES

- The indicated mileage is calculated for flat surfaces. A porous or imperfect surface will require more material in order to cover the same mileage.
- The indicated viscosity is for clear product only. Any addition of colorant may affect the viscosity.

MIX RATIO
1A : 1B

ICETHIN
TECHNICAL DATA SHEET

1



APPLICATION

In a dry, clean container mix 1 part of resin with 1 part of hardener. Stir well along the inner wall of the container and then let it stand for 3-5 minutes. According to the operation time and dosage, adjust the amount of glue to avoid waste.

When the relative humidity is greater than 85%, the surface of the cured product easily absorbs moisture in the air to form a white mist. Therefore, when the relative humidity is greater than 85%, it is not suitable for curing at room temperature. It is recommended to use warm curing. If it is to be ground, it needs to be 3 days after it is fully cured.

CLEANING

Clean all application equipment with acetone. Once the product has hardened, it can only be removed by sanding. It is advisable to clean immediately after use.

RESTRICTIONS

- ICETHIN should be stored in a dry place between 59 - 70°F (15 - 21°C), out of the sun and out of reach of children.
- Resin and hardener should not be left in an open container.
- Application should be used where humidity is under 60% and temperature is between 59 - 70°F (15 - 21°C).
- Use a de-humidifier if needed.
- ICETHIN should be used within one year of purchase.

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult with a doctor. For respiratory problems, transport victim to fresh air. Remove contaminated clothes and clean before reuse. Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Predict suitable ventilation.

Consult the material safety data sheet for further information.

IMPORTANT NOTICE

All statements, recommendations and technical information contained in this document are accurate to the best knowledge of ICE EPOXY. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. ICE EPOXY assumes no legal responsibility for use upon these data. ICE EPOXY assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product.

We are not responsible of any damaged, transformation or alteration of the wood work, table, charcuterie board or any work that is done with our epoxy. The work done is hand crafted with wood or any other material that can vary in form and shape with humidity and temperature and cause a separation or damaged to the epoxy itself and we don't control those item and or environment. Epoxy has no flexibility and becomes an inert plastic once it's dry. We don't warranty the bondage with the wood. The woodworker needs to take all the precaution possible to solidify is work, make sure the humidity of the wood is below 10% and give all the recommendation to the customer in order to keep the table in good condition. There's no warranty on the UV discolouration of the epoxy. We use UV absorber in order to make the epoxy resist as much as possible to the UV rays.